

High Performance Competitor Product Reference Guide

MFG	PRODUCTS	% VISIBLE LIGHT TRANSMISSION (VLT)	% TOTAL SOLAR ENERGY REJECTION (TSER)	% VISIBLE LIGHT REFLECTANCE (VLR)	% UV REJECTION	THICKNESS (mils)
SunTek	HP 55	60	33	8	99	1.5
Formula One	—	—	—	—	—	—
Llumar	—	—	—	—	—	—
Solar Gard	—	—	—	—	—	—
Madico	Onyx 55	44	44	9	99	1.5
Johnson	—	—	—	—	—	—
ASWF	Performer 60	59	33	8	99	1.5
SunTek	HP 50	52	35	8	99	1.5
Formula One	Comfort 50	52	34	9	99	1.5
Llumar	ATR 50	55	35	8	99	1.5
Solar Gard	HP Charcoal 50	50	40	11	98	1.5
Madico	—	—	—	—	—	—
Johnson	SP 45	47	43	13	99	1.5
ASWF	Performer 50	50	39	8	99	1.5
SunTek	HP 40	44	43	8	99	1.5
Formula One	Comfort 38	38	42	9	99	1.5
Llumar	ATR 40	45	41	8	99	1.5
Solar Gard	HP Charcoal 43	43	50	14	98	1.5
Madico	—	—	—	—	—	—
Johnson	SP 40	40	44	8	99	1.5
ASWF	—	—	—	—	—	—
SunTek	HP 35	38	49	8	99	1.5
Formula One	—	—	—	—	—	—
Llumar	ATR 35	38	44	8	99	1.5
Solar Gard	HP Charcoal 38	36	53	12	98	1.5
Madico	Onyx 35	32	49	7	99	1.5
Johnson	SP 35	34	52	10	99	1.5
ASWF	Performer 35	37	50	8	99	1.5
SunTek	HP 30	30	51	8	99	1.5
Formula One	Comfort 30	28	50	9	99	1.5
Llumar	ATR 30	33	46	8	99	1.5
Solar Gard	HP Charcoal 32	32	53	10	98	1.5
Madico	—	—	—	—	—	—
Johnson	SP 25	25	53	8	99	1.5
ASWF	Performer 30	30	51	8	99	1.5

High Performance Competitor Product Reference Guide

MFG	PRODUCTS	% VISIBLE LIGHT TRANSMISSION (VLT)	% TOTAL SOLAR ENERGY REJECTION (TSER)	% VISIBLE LIGHT REFLECTANCE (VLR)	% UV REJECTION	THICKNESS (mils)
SunTek	HP 20	22	54	8	99	1.5
Formula One	—	—	—	—	—	—
Llumar	ATR 20	26	48	8	99	1.5
Solar Gard	HP Charcoal 22	22	55	7	98	1.5
Madico	Onyx 20	15	55	5	99	1.5
Johnson	SP 20	22	55	8	99	1.5
ASWF	Performer 20	19	54	8	99	1.5
SunTek	HP 15	15	56	8	99	1.5
Formula One	Comfort 15	14	61	8	99	1.5
Llumar	ATR 15	15	50	8	99	1.5
Solar Gard	HP Charcoal 13	13	57	5	98	1.5
Madico	—	—	—	—	—	—
Johnson	SP 15	16	55	6	99	1.5
ASWF	Performer 15	16	56	8	99	1.5
SunTek	HP 5	5	58	8	99	1.5
Formula One	Comfort 5	5	64	8	99	1.5
Llumar	ATR 5	5	63	8	99	1.5
Solar Gard	HP Charcoal 6	6	58	4	98	1.5
Madico	Onyx 5	5	57	5	99	1.5
Johnson	SP 5	6	58	7	99	1.5
ASWF	Performer 5	6	57	6	99	1.5

FormulaOne® and Llumar® are registered brand names of Solulia Inc.
 Solar Gard® is a registered brand name of Bekaert Specialty Films, LLC
 Madico® is a registered brand name of Madico, Inc.
 Johnson Window Films® is a registered brand name of Johnson Laminating & Coating, Inc.
 ASWF® is a registered brand name of Erickson International

The attached chart is to be used for comparison purposes only.
 Competitive information and product specifications obtained from formulaone.com, llumar.com, solargard.com, madico.com, johnsonwindowfilms.com and aswf.com on 2/11/2011